



Atlas Minerals & Chemicals, Inc.



# DATA SHEET

4-1300PI (1-14<sup>2</sup>)  
Supersedes 4-1300PI (5-01<sup>2</sup>)

## CHEMPRUF 1300 Lining System

### DESCRIPTION

CHEMPRUF 1300 Lining System is a glass flake reinforced lining system applied at a thickness of 60 mils (1.5 mm.) to 90 mils (2.3 mm.). Applied to concrete and steel substrates, the CHEMPRUF 1300 Lining System is composed of a **chlorendic anhydride polyester** resin and inert fillers with glass flake reinforcement. The lining system can be used in immersion service to 180°F (82°C) and in intermittent service to 210°F (99°C).

The CHEMPRUF 1300 Lining System is designed for primary or secondary containment applications for tanks, trenches, containment dikes, absorbers, scrubbers and floors. The CHEMPRUF 1300 Lining System may be used as a lining or as a membrane in conjunction with chemically resistant brick sheathing. When used as a membrane, the lining can be used at higher process temperatures.

### CHEMICAL RESISTANCE

The CHEMPRUF 1300 Lining System provides resistance to a wide range of oxidizing and non-oxidizing acids, especially nitric acid to 50% and chromic acid to 50%, salts, organic acids, solvents and bleaches, such as chlorine dioxide. Refer to the CHEMPRUF 1000 SERIES Chemical Resistance Chart, 4-1000, for specific information.

**ChemPruf 1300 Lining System** is a 30 mil (0.8 mm.) to 45 mil (1.1 mm.) trowel applied flake filled basecoat and topcoat of ChemPruf 1300 with a roll applied finisher of ChemPruf 300 or ChemPruf 130.

### CHEMPRUF 1300 LINING SYSTEM Consists of: PRIMER

**ChemPruf VE Primer**, a two-component, brush or roller applied penetrating primer.

### BASECOAT / TOPCOAT

**ChemPruf 1300**, a chlorendic anhydride polyester resin, flake filled basecoat and topcoat each trowel applied at 30 mils (0.8 mm.) to 45 mils (1.1 mm.).

### SMOOTHING LIQUID

**ChemPruf VE Smoothing Liquid**, a one-component, roller applied material used to smooth the basecoat and topcoat surface.

**NOTE:** ATLAS makes it a practice to continuously update and enhance our CCM (Corrosion Resistant Construction Materials) products. For the most recent version of any Data Sheet, please visit our Web site at [www.atlasmin.com](http://www.atlasmin.com).

## PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUE
Tensile Strength, 7 days @ 77°F (25°C)	ASTM D638	2,500 psi. (17.2 MPa)
Compressive Strength, 7 days @ 77°F (25°C)	ASTM C579	9,000 psi. (62.1 MPa)
Flexural Strength, 7 days @ 77°F (25°C)	ASTM C580	3,700 psi (25.5 MPa)
Flexural Modulus of Elasticity	ASTM C580	7.55 x 10 <sup>5</sup> psi. (5,200 MPa)
Heat Deflection Temperature	ASTM D648	168°F (76°C)
Temperature Resistance Immersion, Continual Immersion, Intermittent Dry Heat		180°F (82°C) 210°F (99°C) 350°F (177°C)
Hardness, Barcol		38
Cure Rate @ 77°F (25°C), Max Chemical Resistance		7 days

## FINISHER

**ChemPruf 300**, a two-component chlorendic anhydride polyester resin, brush or roller applied sealer.

**ChemPruf 130**, a two-component, flake filled chlorendic anhydride polyester resin, brush or roller applied sealer.

## AVAILABLE COLORS

**ChemPruf 1300** is available in white and gray.

**ChemPruf 300** is available in white and gray.

**ChemPruf 130** is available in white and gray.

## ADDITIONAL INFORMATION

For specific information pertaining to Surface Preparation, Packaging or Mixing and Application, refer to the following ATLAS literature:

- Surface Preparation Data Sheet (PS-30)
- ChemPruf 1300 Lining System Installation Instructions (I-4-1300)
- ChemPruf 130 Data Sheet (4-130PI)
- Lining System Termination Drawing (4-3000DG)
- Termination at Drain Drawing (4-3001DG)
- Control Joint & Structural Crack Drawing (4-3003DG)
- Horizontal / Vertical Transition Drawing (4-3004DG)
- Pipe Outlets Drawing (4-3005DG)

## SURFACE PREPARATION

The substrate must be structurally sound, clean, dry and free of all contaminants, such as sealers, curing compounds, coatings, oil, dirt, dust and water. Previously applied coatings or paint must be removed.

**Concrete:** The prepared concrete substrate shall have a minimum tensile strength of 250 psi. (1.72 MPa). Concrete surface must be sufficiently cured and comply with moisture testing as prescribed by ACI Test Method 515 R-16 "Dryness of Surface".

Concrete surfaces should be grit blasted to a finish similar to the profile of 100 to 120 grit sandpaper. Cracks in the concrete substrate 1/16" (1.6 mm.) wide or greater must be opened to a minimum 1/4" (6.4 cm.) cleaned, primed and filled with ChemPruf 1300.

**Carbon Steel:** Metal surfaces should be grit blasted to a SSPC-SP5 or NACE #1 white metal blast cleaned surface finish. Profile height must be 3 (0.076 mm.) to 4 mils (0.102 mm.).

## TEMPERATURE DURING APPLICATION

Store all materials referred to in this Data Sheet at 70°F (21°C) to 80°F (27°C) for 24 hours prior to use. Minimum temperature for installation is 65°F (18°C). Do not apply when the relative humidity is greater than 75% or the substrate temperature is less than 5°F (3°C) above the dew point.

## APPLICATION

1. Apply ChemPruf VE Primer with a brush or roller.
2. Trowel apply a 30 mil (0.8 mm.) to 45 mil (1.1 mm.) WFT basecoat of ChemPruf 1300. Roll the surface with a short nap paint roller wetted with ChemPruf VE Smoothing Liquid to orient the flake filler, compact the basecoat and to remove trowel marks. Allow to harden.
3. Trowel apply a 30 mil (0.8 mm.) to 45 mil (1.1 mm.) WFT topcoat of ChemPruf 1300. Roll the surface with a short nap paint roller wetted with ChemPruf VE Smoothing Liquid to orient the flake filler, compact the topcoat and to remove trowel marks. Allow to harden.
4. Apply ChemPruf 300 or ChemPruf 130 with a short nap roller. Depending on service conditions, two coats may be required.

Protect uncured primer, basecoat, topcoat and finisher coat(s) from moisture contamination until minimum cure time is attained.

## INSPECTION

1. Inspect lining for imperfections after basecoat has hardened. Repair defects and imperfections prior to application of the topcoat.
2. When specified or required, spark test for pinholes using 100 volts per mil (0.025 mm.) of lining thickness. Spark testing of ChemPruf 1300 Lining System applied to concrete substrates requires ChemPruf VE Primer with ATLAS<sup>®</sup> Carbon Powder.

## MEMBRANE

When the ChemPruf 1300 Lining System is to be used as a membrane with chemical resistant masonry sheathing, a release agent, such as silicone or paste wax, must be applied to the surface of the lining system. Apply the release agent after the ChemPruf 1300 Lining System has attained the minimum drying time. The use of a release agent allows the masonry sheathing to move independent of the lining system.

## PRODUCT SPECIFICATION

The lining system shall be ChemPruf 1300 Lining System as manufactured by Atlas Minerals & Chemicals, Inc.

**ChemPruf 1300 Lining System**, a chlorendic anhydride polyester resin flake filled basecoat and topcoat, each trowel applied at a nominal thickness of 30 mils (0.8 mm.) to 45 mils (1.1 mm.). Service conditions as determined by the manufacturer may require the application of ChemPruf 300 or ChemPruf 130.

## CLEANING OF TOOLS AND EQUIPMENT

Steel wool, soap and warm water will remove the materials referred to in this Data Sheet from mixing tools and equipment if cleaning is done immediately after use. Solvents, such as methyl ethyl ketone, toluene or xylene, will have to be used after the material has begun to harden. Fully hardened material will have to be removed by mechanical means.

Dispose of residues and wastes in accordance with the directions in the Safety Data Sheets and government regulations.

## STORAGE AND SHELF LIFE

Store all materials in a cool, dry environment and out of direct sunlight. Store all ChemPruf Resins and Hardeners at a temperature between 40°F (4°C) and 60°F (16°C) and protect from freezing. In unopened original containers, ChemPruf 1300 Resin and Hardener and ChemPruf 300 Resin and Hardener have a shelf life of three months; ChemPruf VE Primer Resin and Hardener and ChemPruf VE Smoothing Liquid have a shelf life of approximately five months. ATLAS Carbon Powder can be stored indefinitely.

## MAINTENANCE

Should the liner be damaged in any way, it can be repaired by thoroughly cleaning and reapplying the ChemPruf 1300 Lining System.

## PRECAUTIONS

The materials referred to in this Data Sheet are for Industrial Use Only. They contain materials that present handling and potential health hazards. Consult Safety Data Sheets and the container labels for complete precautionary information.

**TECHNICAL SERVICES**

ATLAS maintains a staff of Technical Service Representatives who are available to assist you with the use of ATLAS products. In the event of difficulties with the application of ATLAS materials, the installation should be stopped immediately and ATLAS' Technical Service Department consulted for assistance.

**WARRANTY**

ATLAS warrants that its products will be free from defects in workmanship and materials under normal use for a period of one (1) year from the date of shipment by ATLAS (provided the products are installed before the expiration of the shelf life). THERE ARE NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR THE PURPOSE FOR THIS PRODUCT WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. ATLAS' LIABILITY FOR ALLEGED BREACH OF THIS WARRANTY SHALL BE LIMITED TO REPAIR OR REPLACEMENT OF THE DEFECTIVE PRODUCT (BUT NOT INCLUDING REMOVAL OF THE DEFECTIVE PRODUCT OR INSTALLATION OF REPLACEMENT PRODUCTS). ATLAS SHALL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES DURING THE WARRANTY PERIOD OR THEREAFTER. **ATLAS' WARRANTY IS VOIDED IF PAYMENT FOR PRODUCT IS NOT RECEIVED IN FULL.**