



CHEMESTER® MORTAR

DESCRIPTION

CHEMESTER MORTAR is an epoxy novolac based vinyl ester resin mortar for chemical resistant brick and tile vessel construction.

TYPICAL USES

CHEMESTER MORTAR is an epoxy novolac based vinyl ester mortar designed for use in the pulp and paper industry, as well as the metal working, chemical and food process industries for joining chemical resistant brick and tiles. Applications in the pulp and paper industry include bleach make up tanks, chlorine dioxide towers and preretention tubs, washers and floors.

CHEMICAL RESISTANCE

CHEMESTER MORTAR has outstanding resistance to many oxidizing and nonoxidizing acids, bleaches, alkalis, solvents and salts. Refer to chemical resistance chart for specific information. CHEMESTER MORTAR meets the requirements of ASTM C395, Standard Specification for Chemical Resistant Resin Mortars.

AVAILABLE COLORS

CHEMESTER MORTAR is available in white or black.

PACKAGING AND COVERAGE

CHEMESTER MORTAR

40 lb. (18.1 kg.) Unit Consisting of:

One - 1-gal. can of Resin (8 lb. [3.6 kg.])
One - bag of Powder (32 lb. [14.5 kg.])

210 lb. (95.3 kg.) Unit Consisting of:

One - 5-gal. pail of Resin (42 lb. [18.1 kg.])
Three - bags of Powder (56 lb. [27.2 kg.]) ea.

ATLAS® T-ADDITIVE*

One - 6.7 oz. (190 g.) can per 40 lb. unit
Five - 6.7 oz. (190 g.) cans per 210 lb. unit
*Thixotropic additive for overhead application.

AMPVAR PRIMER Base**

1-gallon (6 lb. [2.7 kg.]) can
Coverage: Approx. 300 sq. ft. (27.9 m²) per can

5-gallon (29 lb. 10 oz. [13.4 kg.]) pail
Coverage: Approx. 1,480 sq. ft. (137 m²) per pail

**Barrier coat over asphalt membrane.

PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUE
Density	ASTM C905	124 lb./cu. ft. (1.99 g./cc.)
Bond Strength, 7 days @ 77°F (25°C)	ASTM C321	325 psi. (2.24 MPa)
Tensile Strength, 7 days @ 77°F (25°C)	ASTM C307	1,750 psi. (12.1 MPa)
Compressive Strength, 7 days @ 77°F (25°C)	ASTM C579	14,200 psi. (97.9 MPa)
Flexural Strength, 7 days @ 77°F (25°C)	ASTM C580	3,950 psi. (27.2 MPa)
Coefficient of Thermal Exp., in./in./°F (cm./cm./°C)	ASTM C531	1.6 x 10 ⁻⁵ (2.9 x 10 ⁻⁵)
Water Absorption	ASTM C413	0.47%
Temperature Resistance Immersion ClO ₂ Tower		220°F (104°C) 180°F (82°C)
Linear Shrinkage	ASTM C531	0.42%

TEMPERATURE DURING APPLICATION

Store CHEMESTER MORTAR at 70°F (21°C) to 80°F (27°C) for 24 hours prior to use. The best working characteristics of the materials will be attained when the temperature of the substrate, air and CHEMESTER MORTAR are between 65°F (18°C) and 85°F (29°C). Minimum temperature for installation is 60°F (16°C).

MIXING OF THE CHEMESTER MORTAR

The mix ratio of CHEMESTER MORTAR varies depending upon the application:

- A ratio of 100 parts Resin to 350 parts Powder, by weight, is suggested for repointing joints and as a setting bed or full joint mortar for masonry floors and walls.
- A ratio of 100 parts Resin to 400 parts Powder, by weight, is suggested for new construction of tile chest / towers.
- A ratio of 100 parts Resin to 300 parts Powder to 5 parts ATLAS T-ADDITIVE, by weight, is suggested for any overhead pointing, full joint and bed joint installations. The ATLAS T-ADDITIVE enhances the holding characteristics without affecting the working time of the mortar.

Stir the contents of the resin container prior to blending. Mix components by hand using a clean, dry, plastic or metal container and a mason's trowel. For larger batch sizes, a KOL type mixer with a 5-gallon capacity may be used. The mixing speed should be between 60 and 75 RPM. Proportionally increase or

decrease resin and powder quantities to attain larger or smaller batch sizes.

Note: The amount of the powder may be varied slightly to obtain the desired consistency. Decreasing the powder component will decrease the estimated unit coverage and will affect the cure times of the mortar. The amount of powder must be within 5%, by weight, of the suggested amount.

Mix Ratio of 100 parts Resin to 350 parts Powder, by weight, is suggested for repointing joints and as a setting bed or full joint mortar for masonry floors and walls.

The following mixing instructions are for a batch size of 4 lb. 8 oz. (2.0 kg.) or 0.04 ft³ (1.1 liters).

- Place 1 lb. (454 g.) or 14.2 fluid ounces (0.42 liters) of CHEMESTER MORTAR Resin in a mixing container.
- Add approximately 3 lb. 8 oz. (1.6 kg.) or 46 fluid ounces (1.36 liters) of CHEMESTER MORTAR Powder.
- Mix the components for approximately two minutes or until all the powder is thoroughly dispersed.

Mix Ratio, by Weight

CHEMESTER MORTAR Resin 100 parts 1 lb. (454 g.)
 Chemester Mortar Powder 350 parts 3 lb. 8 oz. (1.6 kg.)

Mix Ratio, by Volume

CHEMESTER MORTAR Resin 100 parts 14.2 fl. oz. (0.42 liters)
 Chemester Mortar Powder 323 parts 46 fl. oz. (1.36 liters)

Mix Ratio of 100 parts Resin to 400 parts Powder, by weight, is suggested for new construction of tile chest / towers.

The following mixing instructions are for a batch size of 5 lb. (2.3 kg.) or 0.04 ft³ (1.1 liters).

- Place 1 lb. (454 g.) or 14.2 fluid ounces (0.42 liters) of CHEMESTER MORTAR Resin in a mixing container.
- Add approximately 4 lb. (1.8 kg.) or 53 fluid ounces (1.56 liters) of CHEMESTER MORTAR Powder.
- Mix the components for approximately two minutes or until all the powder is thoroughly dispersed.

Mix Ratio, by Weight

CHEMESTER MORTAR Resin 100 parts 1 lb. (454 g.)
 Chemester Mortar Powder 400 parts 4 lb. (1.8 kg.)

Mix Ratio, by Volume

CHEMESTER MORTAR Resin 100 parts 14.2 fl. oz. (0.42 liters)
 Chemester Mortar Powder 371 parts 53 fl. oz. (1.56 liters)

Mix Ratio of 100 parts Resin to 300 parts Powder to 5 parts ATLAS T-ADDITIVE, by weight, is suggested for any overhead pointing, full joint and bed joint installations.

The following mixing instructions are for a batch size of 4 lb. 1 oz. (1.8 kg.) or 0.03 ft³ (0.9 liters).

- Place 1 lb. (454 g.) or 14.2 fluid ounces (0.42 liters) of CHEMESTER MORTAR Resin in a mixing container.
- Add approximately 3 lb. (1.4 kg.) or 40 fluid ounces (1.17 liters) of CHEMESTER MORTAR Powder.
- Mix the components for approximately two minutes or until all the powder is thoroughly dispersed.
- Slowly add approximately 0.8 oz. (22 g.) or 5 fluid ounces (0.15 liters) of ATLAS T-ADDITIVE. The amount of ATLAS T-ADDITIVE may be increased or decreased to attain desired working characteristic or consistency.
- Continue mixing for approximately two minutes or until all the ATLAS T-ADDITIVE is thoroughly dispersed.

ESTIMATING TABLES - CHEMESTER MORTAR

REPOINTING

Mix Ratio 100 parts Resin to 350 parts Powder

Tile Face Size	Square Feet per Unit													
	1/4" Wide Joint				3/8" Wide Joint				1/2" Wide Joint					
	1/2" Deep		3/4" Deep		1/2" Deep		3/4" Deep		1/2" Deep		3/4" Deep		1" Deep	
	40#	210#	40#	210#	40#	210#	40#	210#	40#	210#	40#	210#	40#	210#
8" x 2-1/4"	55	290	37	190	39	205	26	135	30	160	20	105	15	80
8" x 3-7/8"	79	405	53	275	54	285	36	190	42	220	28	145	21	110
8" x 3-3/4"	77	409	51	270	53	280	35	185	41	215	27	145	20	105
8" x 4"	81	425	54	280	55	290	37	195	43	225	28	150	21	110
8" x 4-1/2"	87	455	58	300	59	310	39	205	46	240	30	160	23	120
9" x 2-1/2"	61	320	40	210	42	225	28	150	33	175	22	115	16	85
9" x 3"	69	365	46	240	48	250	32	165	37	195	25	130	18	95
9" x 4-1/2"	90	475	60	315	62	325	41	215	48	250	32	165	24	125
9" x 4"	84	440	56	290	57	300	38	200	44	235	29	155	22	115
9" x 6"	107	560	71	375	73	385	48	255	56	295	37	195	28	145
9" x 12"	151	790	100	525	102	535	68	355	78	410	52	270	39	205

Material estimating quantities may vary depending on project conditions and application techniques. Material quantities are theoretical and do not include a safety factor.

Mix Ratio, by Weight

CHEMESTER MORTAR Resin	100 parts	1 lb. (454 g.)
Chemester Mortar Powder	300 parts	3 lb. (1.4 kg.)
Atlas T-Additive	5 parts	0.8 oz. (22 g.)

Mix Ratio, by Volume

CHEMESTER MORTAR Resin	100 parts	14.2 fl. oz. (0.42 liters)
Chemester Mortar Powder	278 parts	40 fl. oz. (1.17 liters)
Atlas T-Additive	36 parts	5 fl. oz. (0.15 liters)

TYPICAL WORKING & SETTING TIMES OF THE CHEMESTER MORTAR

Temperature	Working Time	Setting Time
60°F (16°C)	45-55 min.	60-80 min.
70°F (21°C)	25-30 min.	40-45 min.
80°F (27°C)	18-22 min.	25-35 min.
90°F (32°C)	5-10 min.	15-20 min.

WAXING OF BRICK FOR FLOORS

CHEMESTER MORTAR can stain red shale brick during installation. Paraffin wax can be applied to the surface face of the brick to eliminate staining. The wax coating and excess mortar are removed from the surface of the brick by steam cleaning. Use a minimum 60 psi. nozzle pressure for cleaning. Allow approximately 24 hours at 65°F (18°C) or 12 hours at 85°F (29°C) minimum cure time before steam cleaning.

APPLICATION OF THE CHEMESTER MORTAR

POINTING MORTAR: Use standard wall pointing techniques for both new construction, as well as repair of old joints. For new construction with portland cement joints, rake out the joints to a depth of 1/4" (6.4 mm.) minimum and point with CHEMESTER MORTAR. For repointing work, remove deteriorating mortar down to

sound substrate or a minimum depth of 1/4" (6.4 mm.) and point with CHEMESTER MORTAR.

SETTING BED: When using CHEMESTER MORTAR as a bed joint over an asphalt membrane, apply a coat of AMPVAR PRIMER Base (without accelerator) over the membrane and allow it to dry. Typical drying times of AMPVAR PRIMER Base are 2-1/2 hours at 65°F (18°C) or 1 hour at 85°F (29°C). Apply the mortar with a 3/16" V-notched trowel held at a 45 degree angle. Place a sufficient amount of mortar to provide a continuous bond coat to the specified thickness. Do not apply more mortar than can be covered in 10 to 15 minutes at 75°F (24°C).

TILE AND BRICK JOINTS: Install the mortar using conventional bricklaying techniques. Apply mortar to two sides of the brick forming a "V" profile. Place brick on the setting bed and slide it into place to attain a 1/8" (3.2 mm.) wide joint. Strike excess mortar before the mortar begins to set.

FULL JOINT TILE CHESTS AND WALLS: Install the mortar using conventional techniques. Apply mortar to the sides of the tile or brick forming a "V" profile. Place tile or brick to attain a 1/4" (6.4 mm.) to 3/8" (9.5 mm.) wide joint. Strike excess mortar before the mortar begins to set.

OVERHEAD: Install the mortar using conventional techniques.

CLEANING OF TOOLS AND EQUIPMENT

Solvents, such as methyl ethyl ketone, toluene or xylene will remove the materials referred to in this Data Sheet from mixing tools and equipment if cleaning is done immediately after use. Fully hardened material will have to be removed by mechanical means.

ESTIMATING TABLES - CHEMESTER MORTAR**FLOORS / WALLS**

Mix Ratio 100 parts Resin to 350 parts Powder

Brick Size	Installed Thickness	Pieces per Sq. Ft.	1/8" Wide x Full Depth Joint Square Feet per Unit		1/8" Setting Bed & 1/8" Wide x Full Depth Joint Square Feet per Unit	
			40 lb. Unit	210 lb. Unit	40 lb. Unit	210 lb. Unit
6" x 6" x 3/4"	3/4"	3.838	116 sq. ft.	610 sq. ft.	NR	NR
8" x 3-7/8" x 1"	1"	4.431	76 sq. ft.	3400 sq. ft.	NR	NR
8" x 3-7/8" x 1-3/16"	1-3/16"	4.431	64 sq. ft.	335 sq. ft.	19 sq. ft.	100 sq. ft.
8" x 3-7/8" x 1-3/8"	1-3/8"	4.431	55 sq. ft.	290 sq. ft.	18 sq. ft.	95 sq. ft.
8" x 4" x 1-3/8"	1-3/8"	4.297	56 sq. ft.	295 sq. ft.	18 sq. ft.	95 sq. ft.
8" x 4" x 1-1/2"	1-1/2"	4.297	52 sq. ft.	270 sq. ft.	18 sq. ft.	95 sq. ft.
8" x 3-3/4" x 2-1/4"	2-1/4"	4.574	33 sq. ft.	175 sq. ft.	15 sq. ft.	80 sq. ft.
8" x 3-3/4" x 2-1/4"	3-3/4"	7.462	14 sq. ft.	70 sq. ft.	9 sq. ft.	45 sq. ft.
8" x 3-3/4" x 4-1/2"	3-3/4"	3.832	22 sq. ft.	115 sq. ft.	12 sq. ft.	65 sq. ft.
8" x 3-3/4" x 4-1/2"	4-1/2"	4.574	16 sq. ft.	85 sq. ft.	10 sq. ft.	55 sq. ft.
9" x 4-1/2" x 2-1/2"	2-1/2"	3.412	35 sq. ft.	180 sq. ft.	15 sq. ft.	80 sq. ft.
9" x 4-1/2" x 2-1/2"	4-1/2"	4.574	13 sq. ft.	65 sq. ft.	8 sq. ft.	45 sq. ft.
9" x 4-1/2" x 3"	3"	4.574	29 sq. ft.	150 sq. ft.	14 sq. ft.	75 sq. ft.
9" x 4-1/2" x 3"	4-1/2"	4.574	14 sq. ft.	75 sq. ft.	9 sq. ft.	50 sq. ft.

COVE BASE

Mix Ratio 100 parts Resin to 350 parts Powder

Brick Size	Installed Thickness	Pieces per Lin. Ft.	1/8" Wide x Full Depth Joint Square Feet per Unit		1/8" Setting Bed & 1/8" Wide x Full Depth Joint Square Feet per Unit	
			40 lb. Unit	210 lb. Unit	40 lb. Unit	210 lb. Unit
5" H x 6" L x 3/4"	3/4"	1.96	220 lin. ft.	1,175 lin. ft.	NR	NR
5" H x 8" L x 1-3/16"	1-3/16"	1.48	130 lin. ft.	700 lin. ft.	25 lin. ft.	150 lin. ft.
5" H x 8" L x 1-3/8"	1-3/8"	1.48	115 lin. ft.	605 lin. ft.	25 lin. ft.	145 lin. ft.
3-7/8" H x 8" L x 1-3/8"	1-3/8"	1.48	160 lin. ft.	865 lin. ft.	55 lin. ft.	290 lin. ft.
8" H x 3-3/4" L x 2-1/4"	2-1/4"	3.10	45 lin. ft.	250 lin. ft.	20 lin. ft.	110 lin. ft.

Bed Joint over membrane at 1/8": 28 sq. ft. per 40 lb. unit, 148 sq. ft. per 210 lb. unit

TILE CHEST

Mix Ratio 100 parts Resin to 400 parts Powder

Tile Size	Installed Thickness	Pieces per Sq. Ft.	1/4" Wide x Full Depth Joint Square Feet per Unit		3/8" Wide x Full Depth Joint Square Feet per Unit	
			40 lb. Unit	210 lb. Unit	40 lb. Unit	210 lb. Unit
9" x 12" x 1-1/4"	1-1/4"	1.2	66 sq. ft.	346 sq. ft.	44 sq. ft.	235 sq. ft.

Material estimating quantities may vary depending on project conditions and application techniques. Material quantities are theoretical and do not include a safety factor. **KEY:** NR = Not Recommended

Dispose of residues and wastes in accordance with the directions in the Material Safety Data Sheets and government regulations.

STORAGE AND SHELF LIFE

Store all materials in a cool, dry environment. Keep all materials out of direct sunlight. CHEMESTER MORTAR Resin must be stored between 40°F (4°C) and 60°F (16°C). Protect from freezing. In unopened original containers, CHEMESTER MORTAR Resin has a shelf life of approximately four months. CHEMESTER MORTAR Powder and ATLAS T-ADDITIVE have a shelf life of approximately one year.

PRODUCT SPECIFICATION

The mortar shall be CHEMESTER MORTAR as manufactured by Atlas Minerals & Chemicals, Inc. The mortar shall comply with the requirements of ASTM C395. The mortar shall consist of an epoxy novolac vinyl ester resin with a silica filler and be resistant to chlorine dioxide.

PRECAUTIONS

The materials referred to in this Data Sheet are for Industrial Use Only. They contain materials that present handling and potential health hazards. Consult Material Safety Data Sheets and the container labels for complete precautionary information.

Note: Odors from uncured CHEMESTER MORTAR will contaminate certain food, beverage and pharmaceutical products. Removal of these products is necessary during the installation and cure of the

material. Evacuate odors to exterior environment and restrict odors from circulating throughout the building.

TECHNICAL SERVICES

ATLAS maintains a staff of Technical Service Representatives who are available to assist you with the use of ATLAS products. In the event of difficulties with the application of ATLAS materials, the installation should be stopped immediately and ATLAS' Technical Service Department consulted for assistance.

WARRANTY

ATLAS warrants that its products will be free from defects in workmanship and materials under normal use for a period of one (1) year from the date of shipment by ATLAS (provided the products are installed before the expiration of the shelf life). THERE ARE NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR THE PURPOSE FOR THIS PRODUCT WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. ATLAS' LIABILITY FOR ALLEGED BREACH OF THIS WARRANTY SHALL BE LIMITED TO REPAIR OR REPLACEMENT OF THE DEFECTIVE PRODUCT (BUT NOT INCLUDING REMOVAL OF THE DEFECTIVE PRODUCT OR INSTALLATION OF REPLACEMENT PRODUCTS). ATLAS SHALL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES DURING THE WARRANTY PERIOD OR THEREAFTER. **ATLAS' WARRANTY IS VOIDED IF PAYMENT FOR PRODUCT IS NOT RECEIVED IN FULL.**

Note: Atlas makes it a practice to continuously update and enhance our CCM (Corrosion Resistant Construction Materials) products. This may result in slight discrepancies between our printed Data Sheets and the current version. For the most recent version of any Data Sheet, please visit our Web site at www.atlasmin.com

CHEMICAL RESISTANCE OF CHEMESTER® MORTAR (5-42PI)

	80°F	H
Acetaldehyde	N	N
Acetic Acid, to 10%	R	R
Acetic Acid, Glacial	N	N
Alum or Aluminum Sulfate	R	R
Aluminum Chloride, Nitrate	R	R
Ammonium Chloride, Nitrate, Sulfate	R	R
Ammonium Hydroxide, to 25%	R	C
Amyl Acetate	R	C
Amyl Alcohol	R	C
Aniline	C	N
Aqua Regia	N	N
Barium Chloride, Nitrate, Sulfate, Sulfide	R	R
Barium Hydroxide	R	C
Benzene	R	N
Benzene Sulfonic Acid, 30%	R	R
Benzoic Acid	R	R
Boric Acid	R	R
Bromine Water	N	N
Butyl Acetate	C	N
Butyl Alcohol, normal	R	C
Butyric Acid	R	C
Cadmium Chloride, Nitrate, Sulfate	R	R
Calcium Bisulfite	R	R
Calcium Chloride, Nitrate, Sulfate	R	R
Calcium Hydroxide, to 25%	R	R
Carbon Disulfide	N	N
Carbon Tetrachloride	R	R
Chlorine Dioxide, Water Solution	R	R
Chlorine, Dry or Wet	R	R
Chlorine Water	R	R
Chloroacetic Acid, to 10%	R	C
Chlorobenzene	R	C
Chloroform	N	N
Chromic Acid, up to 20%	R	R
Chromic Acid, 20% to 50%	R	C
Chromic Acid, above 50%	N	N
Citric Acid, to 10%	R	R
Copper Chloride, Nitrate, Sulfate	R	R
Dichloroacetic Acid, 10%	R	C
Dichlorobenzene	R	C
Diethyl Ether	N	N
Ethyl Acetate	N	N
Ethyl Alcohol	R	C
Ethyl Sulfate	R	C
Ethylene Dichloride	N	N
Ethylene Glycol	R	R
Fluosilicic Acid, 30%	R	C

	80°F	H
Formaldehyde	R	R
Formic Acid	R	C
Gasoline	R	R
Glycerine	R	R
Gold Cyanide	R	R
Hexane	R	R
Hydrobromic Acid	R	R
Hydrochloric Acid	R	R
Hydrocyanic Acid	R	R
Hydrofluoric Acid	RA	N
Hydrofluosilicic Acid	RA	N
Hydrogen Peroxide	R	C
Hydrogen Sulfide Gas, Dry or Wet	R	R
Iron Chloride, Nitrate, Sulfate	R	R
Isopropyl Ether	N	N
Kerosene	R	C
Lactic Acid	R	R
Lead Acetate, Nitrate	R	R
Linseed Oil	R	R
Magnesium Chloride, Nitrate, Sulfate	R	R
Magnesium Hydroxide	R	R
Maleic Acid	R	R
Mercuric Acetate	R	R
Methyl Acetate	R	C
Methyl Alcohol	R	C
Methyl Ethyl Ketone	C	N
Methyl Sulfate	C	N
Mineral Oil	R	R
Mineral Spirits	R	R
Muriatic Acid	R	R
Nickel Chloride, Nitrate, Sulfate	R	R
Nitric Acid, to 20%	R	R
Nitric Acid, 20% to 50%	R	C
Nitric Acid, above 50%	N	N
Nitrobenzene	R	C
Oleic Acid	R	R
Oxalic Acid	R	R
Perchloric Acid, to 30%	R	C
Phenol, to 5%	R	R
Phosphoric Acid, to 80%	R	R
Phosphorous Acid	R	R
Phosphorous Trichloride	N	N
Phthalic Acid	R	R
Picric Acid, to 10%	R	R
Potassium Bicarbonate, Carbonate	R	R
Potassium Chloride, Nitrate, Sulfate	R	R
Potassium Cyanide	R	R

	80°F	H
Potassium Ferricyanide, Ferrocyanide	R	R
Potassium Hydroxide, to 25%	R	C
Potassium Hydroxide, above 25%	R	C
Pyridine	N	N
Rochelle Salt	R	R
Salicylic Acid	R	R
Silver Nitrate	R	R
Sodium Acetate, Bicarbonate, Carbonate	R	R
Sodium Chloride, Nitrate, Sulfate	R	R
Sodium Cyanide, 10%	R	R
Sodium Hydroxide, to 25%	R	R
Sodium Hydroxide, above 25%	R	C
Sodium Hypochlorite, to 15%	R	R
Sodium Hypochlorite, above 15%	R	C
Sodium Sulfide, Sulfite, Thiosulfate	R	C
Soya Oil	R	R
Stearic Acid	R	R
Sulfur Dioxide Gas, Dry or Wet	R	R
Sulfur Trioxide Gas, Dry	R	R
Sulfur Trioxide Gas, Wet	R	R
Sulfuric Acid, to 50%	R	R
Sulfuric Acid, to 70%	R	C
Sulfurous Acid, to 10%	R	R
Tannic Acid	R	R
Tartaric Acid	R	R
Tin Chloride, Sulfate	R	R
Toluene	R	C
Trichloroethylene	N	N
Trisodium Phosphate	R	R
Tung Oil	R	R
Urea	R	R
Xylene	C	N
Zinc Chloride, Nitrate, Sulfate	R	R

KEY

H - Up to temperature limitations of the cements. In cases where chemical boils below this limitation, resistance is intended to be shown up to the boiling point.

R - Recommended

RA - Carbon filled material to be used.

N - Not Recommended

C - Conditional. May be serviceable if the contaminant is immediately removed or washed off the surface.

Note - The information presented in the chemical resistance tables is based on judgments derived from laboratory testing and field service performance. The tables have been prepared as a guide to performance. No guarantee of results is made or implied and no liability in connection with this information is assumed. Contact with free chlorine and chlorine bleaches may cause the surface of CHEMESTER MORTAR, Black, to turn white. This color change will not affect the chemical resistance. The information presented herein should be supplemented by in-service testing. The data furnished in the tables may be revised on the basis of further testing.

(6-037)